


CEWELD MA SS 2367

TYPE	Solid welding wire for hardfacing and rebuilding hotworking tools.				
ANWENDUNGEN	Rebuilding and hardfacing parts that are subject to abrasion combined with higher temperatures up to 550°C				
EIGENSCHAFTEN	Abrasion combined with higher temperatures.				
KLASSIFIKATION	EN ISO W.Nr.	14700: S Fe 13 1.2367			
GEEIGNET FÜR	Hotworking tools, high speed tool steels, HSS, aluminium press molts, dies, stamping tools, cutting tools, shear blades, cutters, knives, scissors.				
ZULASSUNGEN					
SCHWEISSPOSITIONEN					
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	C 0.2	Mn 0.6	Cr 6.2	Mo 3.2	Fe Rem.
MECHANISCHE GÜTEWERTE	Heat Treatment As Welded	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness 45 HRc
RÜCKTROCKNUNG	Not required				
GAS ACC. EN ISO 14175	M11				



CEWELD MA SS 2367

MA SS 2367 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663401823