



CEWELD ER 90S-B3 Tig

TYPE	Tig welding rod for creep resistant A387 P21 and P22 grades.						
APPLICATIONS	CEWELD® ER 90S-B3 Tig exhibits a bainitic microstructure in the tempered and tempered condition. It is used for processing high-temperature steels in High pressure boiler steels, offshore, repair, construction, pipelines, tubing etc						
PROPERTIES	CEWELD® ER 90S-B3 has an extremely easy-to-weld rod with excellent welding properties. It typically contains 2.25 % chromium and 1.0 % molybdenum. Weldable with Co2 and mixed gas. Suitable for heat-resistant applications at working temperatures up to 600 °C. The filler metal has low levels of tramp elements (eg. Sn, As, Sb and P) providing a low Bruscato Factor.(X<10 ppm)for temper embrittlement resistant applications.						
CLASSIFICATION	AWS	A 5.28: ER 90S-B3					
	EN ISO	21952-B: W 2C1M					
	F-nr	6					
	FM	3					
SUITABLE FOR	2,25% Cr, 1% Mo ISO 15608: ~5,2 (1,5 % < Cr < 3,5 % und 0,7% 1.7015, 1.7131, 1.7147, 1.7276, 1.7281,1.7380, 1.7337, 1.7262, 1.7258, 1.7350, 1.7357, 1.7375, 1.7379, 1.7380, 1.7383, 1.7385, 1.7707, 1.8075 10CrMo9-10, 10CrMo11, 12CrMo9-10, 10CrSiMoV7, 12CrSiMo8, 30CrMoV9, GS-18CrMo9.10, 15CrMoV5-10, 16CrMo4-4, 15CrMo5, 24CrMo5, 22CrMo4-4, GS-17CrMo5-5, 15Cr3, 16MnCr5, 20MnCr5, 10CrSiV7, ASTM: A 387 Gr. 22, A217 Grade WC9, A335 Gr. P22, A217 Gr. WC9, A182 F22, A182 T22, A1031 Gr.5015, A1031 Gr.5115, A1031 Gr.4820						
APPROVALS	CE						
WELDING POSITIONS							
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Mo		
	0.09	0.5	0.55	2.5	1.1		
MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					RT	0°C	
	As Welded	500	610	23	150	60	HRC
REDRYING	Not required						
GAS ACC. EN ISO 14175	I1						



CEWELD ER 90S-B3 Tig

ER 90S-B3 TIG 1,6 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663416803

ER 90S-B3 TIG 2,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663416827

ER 90S-B3 TIG 2,4 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663416841

ER 90S-B3 TIG 3,2 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663416858